



Test Report

Report No.: SZC14022581781-7

Date: Mar. 4, 2014

Page 1 of 3

Applicant: DONG GUAN NEW ORIENTAL TECHNOLOGY CO.,LTD

Address: North gate Lane Longhe Industrial Park Tianxin Village Huangjiang Town Dongguan City China

Report on the submitted sample(s) said to be:

Sample Name: ZY-850A(810A/820A/830A/840A/860A/870A/880A/890A)

Sample Description: Translucent white silicone rubber

Sample No.: QT1402258178103

Sample Received Date: Feb. 25, 2014

Testing Period: Feb. 25, 2014 - Mar. 4, 2014

Test Requested: With reference to the demand of extractives as US FDA 21 CFR 177.2600 - Rubber articles intended for repeated use.


Test Method: Please refer to the following page(s).

Test Result: Please refer to the following page(s).

Checked by


Angela

Signed for and on behalf of HCT


Jason
Laboratory Manager

Test Report

Report No.: SZC14022581781-7

Date: Mar. 4, 2014

Page 2 of 3

Test Results:

Unit: mg/inch²


Test Items	Test Condition	MDL	Result	Limit
Extractives of distilled water	Reflux for 7h	0.5	N.D.	20
	Continue to extract, 2h	0.5	N.D.	1
Extractives of n-hexane	Reflux for 7h	0.5	15.8	175
	Continue to extract, 2h	0.5	1.3	4

Note: MDL = method detection limit

N.D. = not detected (less than method detection limit)

mg/inch² = milligram per square inch

Test Flow Chart



Tested by: Shuai Yang

Checked by: Gang Wang



Test Report

Report No.: SZC14022581781-7

Date: Mar. 4, 2014

Page 3 of 3

The photo of the sample



End

This report is considered invalidated without the Special Seal for Inspection of the HCT, This report shall not be altered, increased or deleted. The results shown in this test report refer only to the sample tested. Without written approval of HCT, this report shall not be copied except in full and published as advertisement.